

Title	Organic solar cells using few-walled carbon nanotubes electrode controlled by the balance between sheet resistance and the transparency					
Author(s)	Feng, Yiyu; Ju, Xiaohui; Zhang, Hongbo et al.					
Citation	Applied Physics Letters. 2009, 94(12), p. 123302-123302					
Version Type	VoR					
URL	https://hdl.handle.net/11094/75664					
rights						
Note						

The University of Osaka Institutional Knowledge Archive : OUKA

https://ir.library.osaka-u.ac.jp/

The University of Osaka

Organic solar cells using few-walled carbon nanotubes electrode controlled by the balance between sheet resistance and the transparency

Cite as: Appl. Phys. Lett. **94**, 123302 (2009); https://doi.org/10.1063/1.3103557 Submitted: 06 January 2009 . Accepted: 24 February 2009 . Published Online: 25 March 2009

Yiyu Feng, Xiaohui Ju, Wei Feng, Hongbo Zhang, Yingwen Cheng, Jie Liu, Akihiko Fujii, Masanori Ozaki, and Katsumi Yoshino



ARTICLES YOU MAY BE INTERESTED IN

Organic solar cells with carbon nanotube network electrodes Applied Physics Letters **88**, 233506 (2006); https://doi.org/10.1063/1.2209887

Conducting and transparent single-wall carbon nanotube electrodes for polymer-fullerene solar cells

Applied Physics Letters 87, 203511 (2005); https://doi.org/10.1063/1.2132065

Organic solar cells with carbon nanotubes replacing In_2O_3 : Sn as the transparent electrode Applied Physics Letters 88, 233503 (2006); https://doi.org/10.1063/1.2210081





Appl. Phys. Lett. **94**, 123302 (2009); https://doi.org/10.1063/1.3103557 © 2009 American Institute of Physics.

Organic solar cells using few-walled carbon nanotubes electrode controlled by the balance between sheet resistance and the transparency

Yiyu Feng,^{1,2} Xiaohui Ju,^{1,3} Wei Feng,^{1,a)} Hongbo Zhang,² Yingwen Cheng,² Jie Liu,² Akihiko Fujii,³ Masanori Ozaki,³ and Katsumi Yoshino^{3,4}

School of Materials Science and Engineering and Tianjin Key Laboratory of Composite

and Functional Materials, Tianjin University, Tianjin 300072, People's Republic of China

²Department of Chemistry, Duke University, Durham, North Carolina 27708, USA

³Division of Electrical, Electronic and Information Engineering, Graduate School of Engineering,

⁴Shimane Institute for Industrial Technology, Hokuryo-cho, Matsue, Shimane 690-0816, Japan

(Received 6 January 2009; accepted 24 February 2009; published online 25 March 2009)

Organic photovoltaic devices (OPD) using high conductive transparent few-walled carbon nanotubes (FWNT) film prepared by spraying was fabricated as a selective hole collection. Photovoltaic response with different sheet resistance (R_s) and the transparency (T) of FWNT film was investigated. Maximum efficiency of OPD up to 0.61% with the structure of FWNT (T=70%, $R_s=86 \ \Omega/\Box$)/poly(3-hexylthiophene): [6-6]phenyl-C₆₁-butyric acid methyl ester/Al demonstrates a promising alternative of ITO (0.68%) with almost identical operation. The performance improvement results from the optimal balance between sheet resistance and transparency with three-dimensional network interface between nanotubes and polymers. © 2009 American Institute of Physics. [DOI: 10.1063/1.3103557]

Organic photovoltaic devices (OPDs) are being pursued as a viable alternative to inorganic devices due to low cost and scale-up production.¹ The conventional anode, indium tin oxide (ITO), bears a number of deficiencies including high temperature deposition and inflexibility. Recently, the focus shifts to the integration of carbon nanotubes (CNTs) thin film into OPD (Ref. 2) due to easy solution-processing fabrication and high flexibility. Single-walled CNTs (SWNT) films on glass or poly(ethylene terephthalate) (PET) were investigated.^{2,3} Theoretically the work function of SWNT (4.8–5.0 eV) is sufficiently high to ensure the hole collection leading to better photovoltaic response.⁴ However the best device using CNTs anode³ was still lower than that of ITO. Thus the balance between the transparency and sheet resistance is crucial to OPD optimization. Previous works were focused on the device using SWNT film with the specific transparency and sheet resistance.^{2,3} No detailed reports emerged concerning the changing properties by different sheet resistance and the transparency of CNTs electrode. In this letter, a series of high conductive few-walled CNTs (FWNT) films were utilized as the electrode in bulkheterojunction OPD. Results indicated OPD performance was dependent on the sheet resistance and transparency of FWNT electrode. Optimal OPD using FWNT film (T=70%, $R_s = 86 \ \Omega/\Box$) as a hole collective contact with the efficiency of 0.61% almost operated identically well to the devices using ITO (0.68%).

Highly purified FWNT (Ref. 5) was processed by gas oxidation, H_2O_2 solution⁶ and refluxed in hydrochloric acid (HCl). Transmission electron microscopy (TEM) images of FWNT with double, triple, quadruple, or quintuple walls (indicated by arrow) were shown in Fig. 1. Purified samples

were well dispersed in 0.1% sodium dodecyl sulfate via the ultrasonication. Five FWNT films with different transparency and sheet resistance were prepared by spraying. Uniform FWNT transparent film was obtained by the oxidation.

The variation in sheet resistance (Keithley four-probe measurements) versus the transparency (Varian Cary 500 UV-visible-Near—infrared spectrometer) at 550 nm (a) before and (b) after 2 h HNO₃ treatment is plotted in Fig. 2. HNO₃ treatment reduced the resistance dramatically with slight increase in the transparency due to the increase in the delocalized carrier density through intertube junction by the removal of surfactant using redox dopants.⁷ FWNT films with R_s of 70, 86, and 160 Ω/\Box at the corresponding *T* of 60%, 70%, and 80% were obtained. Both two curves reveal the dependence of the decreased sheet resistance on the cost of the transparency. Importantly the tenfold decrease in



FIG. 1. TEM images of FWNT. Arrows indicate double, triple, quadruple, or quintuple side walls.

Osaka University, 2-1 Yamada-oka, Suita, Osaka 565-0871, Japan

^{a)}Author to whom correspondence should be addressed. Electronic mail: weifeng@tju.edu.cn.



FIG. 2. (Color online) The variation in sheet resistance vs the transparency of FWNT film at 550 nm (a) before and (b) after 2 h HNO₃ treatment.

resistance is accompanied with \sim 1.5-fold increase in the transparency. Therefore, it is critical to build the trade-off between sheet resistance and the transparency of FWNT anode for OPD optimization.

Figure 3 shows scanning electron microscope (SEM) (FEI XL30) images of the continuous FWNT film consisting of micron-length nanotubes parallel deposited on the substrate. Few remaining surfactant (white spot) on FWNT film lower the contact resistance among the cross-junction. Figure 4 shows the optical absorption spectra of (a) FWNT transparent film and (b) FWNT/poly(3-hexylthiophene) (P3HT): [6-6] phenyl-C₆₁-butyric acid methyl ester (PCBM) film. FWNT mostly absorbs the light at the wavelength shorter than 360 nm. It is considered that a large portion of excitons at this region is surpassed by FWNT electrode. The solar cell of P3HT:PCBM showed high External Quantum Efficiency value of 350-600 nm quenching sharply at the wavelength shorter than 350 nm.⁸ Thus light penetration to active layer of P3HT:PCBM mostly covers the wavelength of 350-650 nm.

FWNT transparent film was prepared on glass slide. P3HT and PCBM active layer was spin coated with annealing. Conjugated polymers were free to diffuse and fill in the open porosity of FWNT film.⁹ Al top electrode ($\sim 100 \text{ nm}$) was evaporated under high vacuum. Figure 5 plotted the current versus voltage (J/V) (Keithley 237 high voltage source generator under AM1.5 illumination) characteristic with P3HT:PCBM as active layer using FWNT film of (a) the transparency T=85%, (b) T=80%, (c) T=60%, (d) T=70%, and (e) ITO as the anode. Short current (J_{sc}) , open voltage $(V_{\rm oc})$, fill factor (FF), and efficiency (η) were schemed in Table I. Generally, a trend of the characteristic improvement with the decrease in sheet resistance is indicated at high transparency.² This trend achieves the maximum at T=70%. The optimal performance fabricated by FWNT (T=70%, R_s =86 Ω/\Box)/P3HT:PCBM/A1 exhibits J_{sc} =4.46 mA/cm², $V_{\rm oc}$ =360 mV, FF=0.378, and η =0.61%. This compares



FIG. 3. SEM images of high conducting transparent FWNT film on glass slide. Arrows show the vacancy of the film infiltrated by polymers.



FIG. 4. (Color online) Optical absorption spectra of (a) FWNT transparent film and (b) FWNT/P3HT:PCBM film.

well the devices using ITO (η =0.68%) and surpasses the device without ITO and poly(3,4–ethylenedioxythiophene).² In addition, the device using FWNT electrode (T=60%, R_s =70 Ω/\Box) shows slightly decreased properties (J_{sc} =4.34 mA/cm², V_{oc} =350 mV, FF=0.368, and η =0.56%) due to reduced light absorbing, different from the previous result showing best properties with the lowest resistance of 282 Ω/\Box at T=40%.² Results reveal low sheet resistance is fundamentally vital to the properties as well, and the transparency is also a considerate effect with a harvest of excitons creation. Therefore, the optimal balance plays a significant important role in devices improvement.

Optimal device using FWNT anode might be attributed to three-dimensional (3D) network of FWNT film. Conjugated polymers infiltrate the vacancy and porous FWNT network (black arrows in Fig. 3) when deposited on top. Intimate contact enlarges the interface between FWNT and photoactive polymers leading to efficient holes collection. The infiltration provides sufficient exposure of nanocomposites to the illumination.² This feature efficiently facilitates the exciton creation and dissociation at P3HT/PCBM interface. Therefore, in contrast to planar configuration of ITO, 3D network of FWNT film is beneficial to bulk heterojunction and contribute to the performance enhancement.

In conclusion, we fabricated organic cells using five FWNT films as holes collection. Photovoltaic performance varies from different sheet resistance and the transparency of FWNT electrode. Optimal efficiency up to 0.61% with the structure of FWNT (T=70%, $R_s=86~\Omega/\Box$)/P3HT:PCBM/AI was obtained. The device identically compares well to the cells using ITO (0.68%). Results indicate that FWNT film is



FIG. 5. (Color online) Current density vs voltage (J/V) characteristic of OPD with P3HT:PCBM as active layer using FWNT film of (a) the transparency T=85%, (b) T=80%, (c) T=60%, (d) T=70%, and (e) ITO as the anode.

TABLE I. Current density vs voltage characteristic of OPD of FWNT (ITO)/ P3HT:PCBM/Al with different sheet resistance and the transparency.

	FWNT film		Photovoltaic characteristic			
Devices structure	T (%)	R_s (Ω/\Box)	$\frac{J_{\rm sc}}{({\rm mA/cm^2})}$	V _{oc} (mV)	FF	η (%)
ITO/P3HT:PCBM/Al	89	40	4.87	380	0.367	0.68
	60	70	4.34	350	0.368	0.56
EWNT/D211T.DCDM/A1	70	86	4.46	360	0.378	0.61
FWN1/P3H1:PCBM/AI	80	146	3.91	310	0.338	0.41
	85	235	3.50	290	0.315	0.32

a promising direct alternative to ITO for bulk-heterojunction OPD.

This work was partly supported by the National Natural Science Foundation of China (Grant No. 50873074) and the Program for New Century Excellent Talents in University of Chinese Education Ministry (Grant No. 060232) and the Key Project of Chinese Ministry of Education (Grant No. 108029).

- ¹D. Abdula and M. Shim, ACS Nano 2, 2154 (2008).
- ²A. D. Pasquier, H. E. Unalan, A. Kanwal, S. Miller, and M. Chhowalla, Appl. Phys. Lett. **87**, 203511 (2005).
- ³R. Cicoria and Y. Sun, Nanotechnology **19**, 485303 (2008).
- ⁴M. W. Rowell, M. A. Topinka, M. D. McGehee, H.-J. Prall, G. Dennler, N. S. Sariciftci, L. B. Hu, and G. Gruner, Appl. Phys. Lett. 88, 233506 (2006).
- ⁵S. Suzuki, C. Bower, Y. Watanabe, and O. Zhou, Appl. Phys. Lett. **76**, 4007 (2000).
- ⁶C. Qian, H. Qi, and J. Liu, J. Phys. Chem. C 111, 131 (2007).
- ⁷Y. Y. Feng, H. B. Zhang, Y. Hou, T. P. McNicholas, D. N. Yuan, S. W. Yang, L. Ding, W. Feng, and J. Liu, ACS Nano 2, 1634 (2008).
- ⁸J. L. Blackburn, T. M. Barnes, M. C. Beard, Y. H. Kim, R. C. Tenent, T. J. McDonald, B. To, T. J. Coutts, and M. J. Heben, ACS Nano 2, 1266 (2008).
- ⁹E. Lioudakis, A. Othonos, I. Alexandrou, and Y. Hayashi, J. Appl. Phys. **102**, 083104 (2007).