

Title	Self-Diffusion of Sodium and Potassium in Molten Flinak
Author(s)	Iwamoto, Nobuya; Umesaki, Norimasa; Tsunawaki, Yoshiaki et al.
Citation	Transactions of JWRI. 1978, 7(2), p. 279-281
Version Type	VoR
URL	https://doi.org/10.18910/7624
rights	
Note	

Osaka University Knowledge Archive : OUKA

<https://ir.library.osaka-u.ac.jp/>

Osaka University

Self-Diffusion of Sodium and Potassium in Molten Flinak[†]

Nobuya IWAMOTO*, Norimasa UMESAKI**, Yoshiaki TSUNAWAKI***,
Kazuo FURUKAWA**** and Hideo OHNO****

In the previous paper¹⁾, the authors reported the self-diffusion coefficients of fluorine and lithium in molten LiF-NaF-KF (46.5:11.5:42.0 mole%) eutectic mixture (Flinak) with the improved capillary reservoir technique using ¹⁸F and ⁶Li tracers. The diffusion coefficients of fluorine and lithium in molten Flinak are smaller than those of other molten alkali halides, in spite of similar values of D_0 (independent term of temperature) and E_D (activation energy) for diffusion in molten Flinak as those molten alkali halides.

In this note, the self-diffusion coefficients of sodium and potassium in molten Flinak are reported. The diffusion coefficients were measured with the same experimental technique in temperature range of 491–616°C with the use of ²²Na and ⁴²K as tracer. Figure 1 shows the diffusion coefficients of sodium, potassium, fluorine¹⁾ and lithium¹⁾, in molten Flinak. The results can be expressed in term of

$$D = D_0 \exp(-E_D/RT) \quad (1)$$

, where D denotes the diffusion coefficient (cm²/sec), D_0 the independent term of temperature, E_D the activation energy (kcal/mole), R the gas constant, and T the absolute temperature, respectively. Table 1 shows the constants of equation (1) calculated with least square means for fluorine¹⁾, lithium¹⁾, sodium and potassium. The diffusion coefficients of anion and cations in molten

Table 1 Constants of equation (1) for fluorine, lithium, sodium and potassium in molten Flinak.

Salt	Tracer	$D_0 \times 10^3$ (cm ² /sec)	E_D (kcal/mole)	Temp. range °C	E_D/RT_m
Flinak	¹⁸ F	1.63	7.23	480-663	5.01
	⁶ Li	3.85	8.88	480-663	6.15
	²² Na	4.42	8.70	504-616	6.02
	⁴² K	0.729	6.06	491-613	4.20




Fig. 1 Self-diffusion coefficients of fluorine, lithium, sodium and potassium in molten Flinak.

Flinak took almost similar values within experimental error.

If the diffusion phenomena in molten Flinak are governed with jumping and exchanging of anion and cation, it is thought that the diffusion will be affected by size and number of ionic species. In Table 2, the values such as ionic fraction, ionic radius and volume ratio of

[†] Received on October 16th, 1978

* Professor

** Graduate Student, Osaka University

*** Lecturer

**** Japan Atomic Energy Research Institute

Table 2 Values of ionic fraction, ionic radius and volume ratio of anion and cations in molten Flinak.
 r_+ and r_- are the ionic radius of cation and anion.

Salt	Ionic fraction	Ionic radius	$(r_+/r_-)^3$
Flinak	F	0.5000	1.36
	Li	0.2325	0.60
	Na	0.0575	0.95
	K	0.2100	1.33

various anion and cations in molten Flinak are compared. With the comparison of these values and obtained results, it is thought that the diffusion coefficients in molten Flinak are not necessarily influenced by the ionic radii or number of ionic species.

Generally, it can be accepted that each ion in molten Flinak is surrounded by oppositely charged ions. Therefore it can be considered that the jump of individual ion for a rearrangement is controlled with cation-anion electrostatic attraction with the following equation,

$$I = Z^+ Z^- e^2 / r^2 \quad (2)$$

, where Z^+e and Z^-e are charge of cation and anion, r sum of cation and anion radii ($r = r_+ + r_-$). Accordingly, the activation energy E_D for diffusion will be proportion to the cation-anion electrostatic attraction I , $E_D \propto I$. Figure 2 shows the comparison of E_D with I in molten




Fig. 2 Comparison of the activation energy E_D for diffusion with cation-anion electrostatic attraction I in molten Flinak, $\text{NaF}^{(2)}$ and $\text{KF}^{(2)}$. ●, Flinak; △, Na in NaF; ◇, K in KF.

Flinak, $\text{NaF}^{(2)}$ and $\text{KF}^{(2)}$. It is evident that the value of E_D increases with increasing of I . The size effect of an

ion for diffusion generally decreases with increasing of the interaction between anion and cation. It is, therefore, concluded that in molten Flinak the size effect is depressed by the interaction of individual ion, because the observed diffusion coefficients of each ion are almost equal. According to Sjöblom³⁾, the value of E_D/RT_m , where T_m is the melting point in degree Kelvin, is more than 4.0 for the salts considered as forming complex anions in the metl. As arithmetic mean value of E_D/RT_m of molten Flinak is about 5.3 in table 1, it is anticipated that the interaction between anion and cation in molten Flinak is strong.

Furthermore, there exists the correspondence between diffusion and electrical conductance with the following relation called as Nernst-Einstein equation,

$$D_i = \Lambda_i R T / Z_i F \quad (3)$$

, where Λ_i denotes the equivalent conductance, Z_i the charge of species i , and F the Faraday constant. Figure 3 shows the comparison of the observed diffusion coefficients with those calculated from electrical con-




Fig. 3 Comparison of the observed diffusion coefficients with those calculated from electrical conductance⁴⁾ in molten Flinak.

ductance⁴⁾ according to equation (3). The observed diffusion coefficients take value 20% excess on an average at same temperature. It seems that the diffusion processes without charge transfer contribute in molten Flinak in the same way as other molten alkali halides.

Figures 4 and 5 show the comparison of diffusion coefficients of fluorine, lithium, sodium and potassium in molten Flinak with those of anions and cations in other




Fig. 4 Comparison of the self-diffusion coefficients of fluorine in molten Flinak with those of anions in other molten alkali halides under the reduced temperature scale T/T_m . M.D. shows the diffusion coefficients calculated by molecular dynamics.

molten alkali halides under the reduced temperature scale T/T_m . It is recognized that the diffusion coefficients of fluorine, lithium, sodium and potassium in molten Flinak are smaller than those of anions and cations in other molten alkali halides. These results will support our discussion of diffusion mechanism in molten Flinak in the previous paper¹⁾.




Fig. 5 Comparison of the self-diffusion coefficients of lithium, sodium and potassium in molten Flinak with those of cations in other molten alkali halides under the reduced temperature scale T/T_m . M.D. shows the diffusion coefficients calculated by molecular dynamics.

References

- 1) N. Iwamoto, Y. Tsunawaki, N. Umesaki, K. Furukawa and H. Ohno: Trans. JWRI, 7 (1978), p.5.
- 2) K. Grjotheim and S. Zuca: Acta Chem. Scand., 32 (1968), p.531.
- 3) C. A. Sjöblom: Z. Naturforsch., 23a (1968), p.933.
- 4) S. I. Choen, W. D. Powers and N. D. Greene: ORNL-2150 (1956), p.22.