

Title	Electric Field Analysis of Defect Mode in Cholesteric Liquid Crystal Constructed with Different Periodicities
Author(s)	Ozaki, Ryotaro; Sanda, Takuji; Yoshida, Hiroyuki et al.
Citation	電気材料技術雑誌. 2005, 14(2), p. 11-14
Version Type	VoR
URL	https://hdl.handle.net/11094/76793
rights	
Note	

The University of Osaka Institutional Knowledge Archive : OUKA

https://ir.library.osaka-u.ac.jp/

The University of Osaka

## Electric Field Analysis of Defect Mode in Cholesteric Liquid Crystal Constructed with Different Periodicities

Ryotaro Ozaki<sup>1)</sup>, Takuji Sanda<sup>2)</sup>, Hiroyuki Yoshida<sup>2)</sup>, Yuko Matsuhisa<sup>2)</sup>, Masanori Ozaki<sup>2)</sup> and Katsumi Yoshino<sup>2),3)</sup>

1) Department of Electrical and Electronic Engineering, National Defense Academy,

1-10-20 Hashirimizu, Yokosuka, Kanagawa 239-8686, Japan

Tel: +81- 46-841-3810 (ext. 3354), Fax: +81-46-844-5903, E-mail: ozaki@nda.ac.jp

2) Department of Electronic Engineering, Graduate School of Engineering, Osaka University,

2-1 Yamada-oka, Suita, Osaka 565-0871, Japan

3) Research Project Promotion Institute, Shimane University, 2 Hokuryo-cho, Matsue, Shimane 690-0816, Japan

Photonic crystals (PCs) having a three-dimensional ordered structure with a periodicity of optical wavelength has attracted considerable attention from both fundamental and practical point of view, because in such materials, a photonic band gap exists in which the existence of a certain energy range of photon is forbidden, and various applications of PCs have been proposed.<sup>1,2</sup> Particularly, the study of stimulated emission in the photonic band gap, a spontaneous emission is inhibited and low-threshold lasers based on photonic crystals are expected. In a one-dimensional (1D) periodic structure, laser action has been expected at the photonic band edge where the photon group velocity approaches zero.<sup>3</sup>

Liquid Crystals (LCs) including chiral molecules have a self-organized helical structure which can be regarded as a 1D periodic structure. In such system, there is a so-called stop band in which a light cannot propagate, which is considered a 1D pseudo-bandgap. Lasing at the band edge has been reported in cholesteric liquid crystal (CLC), chiral smectic LC and polymerized CLC.<sup>4-7</sup> These laser actions in the 1D helical structure of the chiral LCs are interpreted to be based on the band edge of the 1D photonic band gap in which the photon group velocity is suppressed.

On the other hand, a localization of a light based on a defect mode caused by an imperfection in the periodic structure has been expected as potential applications such as low-threshold lasers and microwavegides. In the chiral LC, several new type defect modes have been proposed. For example, an introduction of an isotropic defect layer into the periodic helical structure of the CLC has been theoretically studied.<sup>8</sup> From a concept of a phase jump, an existence of a twist defect which is a discontinuous point of the periodic helical structure has been predicted.<sup>9</sup> In this system, we have experimentally demonstrated the defect mode in the 1D photonic band gap of the CLC having the twist defect by using photopolymerized CLC (PCLC) films, and the laser action based on the twist defect mode has also been observed in the dye-doped PCLC composite film with the twist defect.<sup>10</sup> The defect mode caused by a partial deformation of the helix in the CLC has been proposed.<sup>11</sup> In this model, an optically induced local modulation of helical twisting power is used as a method to induce a helix defect, which can be achieved by photochemical effects. In a hybrid system consisting a nematic and a cholesteric LC, a phase retardation defect mode have been demonstrated by an introduction of a nematic LC defect layer into the PCLC.<sup>12</sup>

In this paper, we have studied the defect mode in the 1D photonic band gap of the CLC consisting two helicoidal periodicities. Optical properties of the CLC consisting two helicoidal periodicities have been analyzed by calculating electromagnetic wave transmission.

Figure 1 shows a schematic view of the CLC consisting two helicoidal periodicities. In this study,  $CLC_1$  and  $CLC_2$  are defined as both sides CLCs and a center part, respectively. The helical pitch of  $CLC_2$  is shorter than the  $CLC_1$ , but refractive indices of the  $CLC_1$  and  $CLC_2$  are equivalent. Therefore, the variation of  $CLC_2$  from  $CLC_1$  is only the helical pitch.

In order to investigate optical properties of CLC, we have performed a theoretical calculation of the light propagation in the CLC consisting two helicoidal periodicities by using a 4x4 matrix. This method is a numerical analysis of Maxwell equations which can quantitatively calculate the light propagation in a medium with a refractive index varying along one direction. The light propagating along the z-axis with frequency  $\omega$  is given by

$$\frac{d\Psi(z)}{dz} = \frac{i\omega}{c} D(z)\Psi(z)$$
(1)

where D(z) is a derivative propagation matrix and  $\Psi(z) = (E_x, H_y, E_y, H_x)^T$ . From this equation, we can obtain transmission or refrection properties of the CLC.

We have also calculated the electric field distribution in the CLC consisting two helicoidal periodicities by using a finite difference time domain (FDTD) method. This calculation is an analysis of Maxwell equations by according to the Yee algorithm in discrete time and lattices. When Maxwell equations of the electromagnetic field propagating in the anisotropic medium along *z*-axis are approximated by finite differences, we obtain

$$E_{x}^{\prime+1}(i) = -\frac{\varepsilon_{yy}\varepsilon_{0}}{\varepsilon_{xx}\varepsilon_{yy} - \varepsilon_{xy}\varepsilon_{yx}}\frac{\Delta t}{\Delta z} \left\{ H_{y}^{T}(j+1) - H_{y}^{T}(j) \right\} - \frac{\varepsilon_{xy}\varepsilon_{0}}{\varepsilon_{xx}\varepsilon_{yy} - \varepsilon_{xy}\varepsilon_{yx}}\frac{\Delta t}{\Delta z} \left\{ H_{x}^{T}(j+1) - H_{x}^{T}(j) \right\} + E_{x}^{\prime}(i)$$
(2)

$$E_{y}^{\prime+1}(i) = -\frac{\varepsilon_{xx}\varepsilon_{0}}{\varepsilon_{xx}\varepsilon_{yy} - \varepsilon_{xy}\varepsilon_{yx}}\frac{\Delta t}{\Delta z} \left\{ H_{x}^{T}(j+1) - H_{x}^{T}(j) \right\} + \frac{\varepsilon_{xy}\varepsilon_{0}}{\varepsilon_{xx}\varepsilon_{yy} - \varepsilon_{xy}\varepsilon_{yx}}\frac{\Delta t}{\Delta z} \left\{ H_{y}^{T}(j+1) - H_{y}^{T}(j) \right\} + E_{y}^{\prime}(i)$$
(3)

$$H_{x}^{T+1}(j) = -\mu_{0} \frac{\Delta t}{\Delta z} \left\{ E_{y}'(i+1) - E_{y}'(i) \right\} + H_{x}^{T}(j)$$
(4)

$$H_{y}^{T+1}(j) = -\mu_{0} \frac{\Delta t}{\Delta z} \left\{ E_{x}'(i+1) - E_{x}'(i) \right\} + H_{y}^{T}(j)$$
(5)

where  $\Delta z$  relating the resolution of the calculation is 2 nm. On both sides of the structure, the following first-order absorbing boundary condition is used. A sinusoidal point optical source is used as the excitation source to incident light into the cell.

Figure 2 shows calculated transmission spectra of single CLC and composite CLC films. Broken lines in Fig. 2 shows calculated transmission spectra of the  $CLC_1$  and the  $CLC_2$  single films. Both the number of the helical pitch of the  $CLC_1$  and the  $CLC_2$  single films is 10, and ordinary and extraordinary refractive indices are 1.5 and 1.7, respectively.



Fig. 1 Cholesteric liquid crystal consisting two helicoidal periodicities.

## 電気材料技術雑誌 第14巻第2号 J.Soc.Elect.Mat.Eng. Vol.14, No.2, 2005

Pitch length of the CLC<sub>1</sub> is 375 nm constantly, but the pitch length of the CLC<sub>2</sub> varies from 350 nm to 360 nm, that is to say, distinctions in Fig. 2 are only pitch length of the CLC<sub>2</sub>. In this condition, stop bands in transmission spectra of the CLC1 and the CLC<sub>2</sub> overlap slightly. Solid line in Fig. 2 shows calculated transmission spectra of the CLC consisting two helicoidal periodicities as shown in Fig. 1. In the composite CLC, the pitch number of the CLC<sub>2</sub> at center and the CLC<sub>1</sub> at one side are 10 and 5, respectively. Since this composite CLC is composed of different pitches, the wide stop band in the transmission spectrum appears. In addition, defect mode peaks caused by the introduction of the CLC<sub>2</sub> layer appear in the stop band. On account of that defect modes are due to resonance between two CLC1 films, defect mode peaks appear in the stop band of the CLC<sub>1</sub> excepted in the overlap with the stop band of the CLC2. It should be noted that defect mode peaks in any condition appear at the band edge wavelength of the CLC<sub>2</sub>. In generally, the defect mode wavelength is determined by the optical length or the phase retardation of the defect layer. However, in the CLC consisting two helicoidal periodicities, defect mode always appears at the band edge wavelength of the CLC<sub>2</sub>.

In order to investigate the origin of the defect mode at the band edge of the  $CLC_2$ , we have also calculated the distribution of the electric field in the CLC consisting two helicoidal periodicities by using the FDTD method. Figure 3 (a) shows the electric field distribution in the CLC consisting two helicoidal periodicities at the band edge wavelength of the CLC<sub>2</sub>, where parameters in this calculation are follow as: the pitch length of CLC<sub>1</sub> and CLC<sub>2</sub> are 375 nm and 350 nm, the incident light was circularly polarized and has the same sign of rotation as the CLC



Fig. 2 Transmission spectra of single and composite CLC films calculated by a 4x4 matrix method as a function of the pitch length of the  $CLC_2$  (P<sub>2</sub>). Upper graph shows calculated transmission spectra of single  $CLC_1$  and single  $CLC_2$ . Lower graph shows calculated transmission spectra of CLC consisting two helicoidal periodicities.

helix. When the incident light wavelength is in the photonic band gap, the electric field of the incident light simply decrease. However, the propagating light through the composite CLC is amplified at the center of the  $CLC_2$ . This is because the incident light arriving at the  $CLC_2$  is amplified by the  $CLC_2$ 's own periodicity. This means that the defect mode origin is not from the resonance between  $CLC_1$ s but from the the band edge effect of the  $CLC_2$ . In other words, the defect mode peak indicates the band edge wavelength of inside CLC in a different form. Figure 3 (b) shows the electric field distribution of in single  $CLC_2$  film at the band edge wavelength. It should be noted that the electric field enhancement in CLC consisting two helicoidal periodicities is stronger than single CLC film. The cause of a high enhancement of composite CLC films is that electric field is amplified by two effects of  $CLC_1$ s as

電気材料技術雑誌 第14巻第2号 J.Soc.Elect.Mat.Eng. Vol.14, No.2, 2005

distributed Bragg reflector and  $CLC_2$  as distributed feedback resonator. Therefore, it is found that a combination of the defect mode and the band edge attains an efficient confinement of the light.

In conclusion, we have studied the optical properties of the CLC consisting two helicoidal periodicities by 4x4 matrix and FDTD methods. One of the defect mode peaks always appeared at the band edge wavelength of  $CLC_2$ . This is because the incident light arriving at the  $CLC_2$  is amplified by the  $CLC_2$ 's own periodicity. In other words, the defect mode peak indicates the band edge wavelength of inside CLC in a different form. Furthermore, it is found that the CLC consisting two helicoidal periodicities is capable of a high electric field enhancement.



Fig. 3 (a) Electric filed distribution of CLC consisting two helicoidal periodicities at the band edge wavelength of the  $CLC_2$ . (b) Electric filed distribution of  $CLC_2$  film at band edge wavelength. These results are calculated by FDTD method.

## References

- [1] E. Yablonovitch, Phys. Rev. Lett., 58 (1987) 2059.
- [2] S. John, Phys. Rev. Lett., 58 (1987) 2486.
- [3] J. P. Dowling, M. Scalora, M. J. Bloemer and C. M. Bowden, J. Appl. Phys., 75 (1994) 1896.
- [4] V. I. Kopp, B. Fan, H. K. M. Vithana and A. Z. Genack, Opt. Lett., 23 (1998) 1707.
- [5] M. Ozaki, M. Kasano, D. Ganzke, W. Haase and K. Yoshino, Adv. Mater., 14 (2002) 306.
- [6] H. Finkelman, S. T. Kim, A. Munoz, and P. Palffy-Muhoray, Adv. Mater., 13 (2001) 1069.
- [7] T. Matsui, R. Ozaki, K. Funamoto, M. Ozaki, and K. Yoshino, Appl. Phys. Lett., 81 (2002) 3741.
- [8] Y.-C. Yang, C.-S. Kee, J.-E. Kim, H. Y. Park, J.-C. Lee and Y.-J. Jeon, Phys. Rev. E, 60 (1999) 6852.
- [9] V. I. Kopp and A. Z. Genack, Phys. Rev. Lett., 89 (2002) 033901.
- [10] M. Ozaki, R. Ozaki, T. Matsui and K. Yoshino, Jpn. J. Appl. Phys., 42 (2003) L472.
- [11] M. H. Song, B. Park, K.-C. Shin, T. Ohta, Y. Tsunoda, H. Hoshi, Y. Takanishi, K. Ishikawa, J. Watanabe, S.
- Nishimura, T. Toyooka, Z. Zhu, T. M. Swager and H. Takezoe, Adv. Mater., 16 (2004) 779.
- [12] T. Matsui, M. Ozaki and K. Yoshino, Phys. Rev. E, 69 (2004) 061715.