

Title	CAD-CAM resin composites: Effective components for further development
Author(s)	Yamaguchi, Satoshi; Li, Hefei; Sakai, Takahiko et al.
Citation	Dental Materials. 2024, 7(Suppl), p. 11
Version Type	VoR
URL	https://hdl.handle.net/11094/94595
rights	This article is licensed under a Creative Commons Attribution 4.0 International License.
Note	

Osaka University Knowledge Archive : OUKA

https://ir.library.osaka-u.ac.jp/

Osaka University

Dental Materials xxx (xxxx) xxx



Contents lists available at ScienceDirect

Dental Materials



journal homepage: www.elsevier.com/locate/dental

CAD-CAM resin composites: Effective components for further development

Satoshi Yamaguchi^{a,*}, Hefei Li^a, Takahiko Sakai^b, Chunwoo Lee^a, Haruaki Kitagawa^a, Satoshi Imazato^a

^a Department of Dental Biomaterials, Osaka University Graduate School of Dentistry, 1-8 Yamadaoka, Suita, Osaka 565-0871, Japan
^b Department of Fixed Prosthodontics and Orofacial Function, Osaka University Graduate School of Dentistry, 1-8 Yamadaoka, Suita, Osaka 565-0871, Japan

ARTICLE INFO	A B S T R A C T
Keywords: CAD-CAM Resin composites Artificial intelligence Finite element analysis Fatigue	Objective: This paper summarizes the effective components of computer-aided design and computer-aided manufacturing (CAD-CAM) resin composites that contribute to achieving greater mechanical properties and further development. Methods: In silico multi-scale analysis, in silico nonlinear dynamic finite element analysis (FEA), and artificial intelligence (AI) were used to explore the effective components of CAD-CAM resin composites. The effects of the filler diameter and silane coupling ratio on the mechanical properties of CAD-CAM resin composites have been clarified through multi-scale analysis. The effects of the filler contents, and filler and monomer compositions have been investigated by AI algorithms. The fracture behavior of CAD-CAM composite crown was analyzed using in silico non-linear dynamic FEA. The longevity of CAD-CAM composite crown was assessed through step-stress accelerating life testing (SSALT). Results: As the filler diameter decreases, there is an increase in elastic moduli and compressive strengths at the macroscale. At the nanoscale, a decrease in the filler diameter results in a decrease in the elastic modulus and compressive strength. According to the exhaustive search and feature importance analysis based on the AI algorithm, the combination of certain components was narrowed down to achieve a flexural strength of 269.5 MPa. The in silico non-linear FEA successfully detected the sign of the initial crack of the CAD-CAM composite molar crown. The SSALT revealed that CAD-CAM resin composite molar crowns containing nanofillers with a high fraction of resin matrix demonstrated great longevity. Significance: This paper summarized the effective components of CAD-CAM resin composites for their further development. The integration of in vitro and in silico approaches will expedite the advancement of CAD-CAM resin composites, offering benefits such as time efficiency

1. Introduction

The success of computer-aided design and computer-aided manufacturing (CAD-CAM) technologies, led by early pioneers such as Mörmann [1], Duret [2], and Rekow [3,4] in the late 1980 s, has dramatically evolved CAD-CAM materials used in dentistry over the past 40 years. These materials include yttria stabilized tetragonal zirconia polycrystals [5,6], lithium silicate glass ceramics [7], and CAD-CAM resin composites [8].

The first machinable CAD-CAM resin composites were fabricated by factory polymerization, and their mechanical properties have been improved through polymerization under varying temperatures and pressures, compared to conventional resin composites for filling [9]. Further improvements in the mechanical properties of CAD-CAM resin composites were achieved through high pressure and temperature polymerization [10]. In 2014, Okada *et al.* [11] invented the filler press and monomer infiltration method to increase the nano-filler content of CAD-CAM resin composites.

In Japan, the restoration of premolars using CAD-CAM composite crowns has been covered by the National Health Insurance system since 2014 [12], and this coverage has been expanded to include the restoration of the first molars in 2017 and the anterior teeth in 2020.

However, despite the evolution of CAD-CAM resin composites and manufacturing techniques, crown fractures and chipping can still occur

* Corresponding author. E-mail address: yamaguchi.satoshi.dent@osaka-u.ac.jp (S. Yamaguchi).

https://doi.org/10.1016/j.dental.2024.01.002

Received 11 December 2023; Received in revised form 6 January 2024; Accepted 9 January 2024 Available online 15 January 2024

0109-5641/© 2024 The Authors. Published by Elsevier Inc. on behalf of The Academy of Dental Materials. This is an open access article under the CC BY license (http://creativecommons.org/licenses/by/4.0/).

S. Yamaguchi et al.

under clinical service, resulting in a limited lifespan for restorations [12, 13]. Additionally, CAD-CAM composite crowns cemented on human dentin tend to induce debonding within six months [12]. According to a retrospective cohort study over four years, 106 out of 362 crowns showed complications, with crown debonding being the most frequent (74.5%), followed by crown fracture (4.7%) and chipping (1.9%) [12]. The main factors for debonding were the vertical dimension of the abutment teeth, the taper of the abutment teeth, and the thickness of the crown occlusion surface [14]. The occlusal load during chewing, in combination with a low elastic modulus or insufficient occlusal thickness of the CAD-CAM composite crown, leads to transverse expansion, which tends to spread the crown margin, leading to the destruction of the adhesive interface [15,16]. Therefore, improving the mechanical properties of CAD-CAM resin composites has always been a topic of great interest.

This paper summarizes the effective components of CAD-CAM resin composites that contribute to achieving greater mechanical properties and further development.

2. In silico approaches in dentistry

To explore the effective components of CAD-CAM resin composites, an *in silico* approach, which involves the use of computer simulation, is useful. This approach can save time and reduce the waste of *in vitro* testing materials that often results from the trial-and-error approach.

Multi-scale analysis, a coupled method for analyzing physical properties or behaviors across different scales, has been used to predict the mechanical properties of CAD-CAM resin composites [17]. Through homogenization, the mechanical properties of CAD-CAM resin composites can be predicted from their nanostructure. This multi-scale analysis is utilized to compare factors such as filler size, composition, and the coupling condition with the resin matrix. By localization, the points of crack initiation at the nanoscale can be predicted by the stress or strain distribution in the CAD-CAM resin composites at the macroscale.

Finite element analysis (FEA) is widely used to assess stress or strain distribution and is a powerful tool for predicting the points of fracture initiation in CAD-CAM composite crowns [18]. However, conventional static FEA or fractographic analysis does not provide a way to represent fracture behavior such as crack propagation or the order of fracture. Thus, Yamaguchi *et al.* [19] have established an *in silico* non-linear dynamic FEA to mimic the *in vitro* fracture behavior observed in a three-point bending test. The combination of *in vitro* and *in silico* approaches is useful for analyzing the fracture behavior of CAD-CAM composite crowns using various preparation designs, loading conditions, and occlusal contacts that coincide with clinical situations [20].

Artificial intelligence (AI) technologies have become widely accepted in society and have been preliminarily implemented in dentistry [21,22]. Machine learning (ML), a subfield of AI, is a powerful tool for finding meaningful regularities in high-dimensional data, which allows for predictions of unknown data [23]. ML has recently become a major tool in the Materials Informatics (MI) research field and has been used for predicting material properties as a solution to a direct problem from unknown features (compositions, experimental conditions, *etc.*) [24].

3. Components of CAD-CAM resin composites

As shown in Fig. 1, factors such as the filler diameter, the silane coupling ratio with the resin matrix, filler contents, and filler and monomer compositions can influence the mechanical properties of CAD-CAM resin composites.

The effects of the filler diameter and silane coupling ratio on the mechanical properties of CAD-CAM resin composites at both the nanoscale and macroscale have been clarified through homogenization and localization. As the filler diameter decreases (from 100 nm to 20 nm),



Fig. 1. Schematic illustration of the components of CAD-CAM resin composites. UDMA: urethane dimethacrylate, TEGDMA: triethylene glycol dimethacrylate.

there is an increase in elastic moduli and compressive strengths, while Poisson's ratios decrease [17] at the macroscale. At the nanoscale, a decrease in the filler diameter results in a decrease in the maximum value of the maximum principal strain [17].

When the silane coupling ratio (the ratio of filler surface coverage) decreases (from 100% to 75.5%), there is a decrease in the elastic modulus and compressive strength [25]. The relationship between the silane coupling ratio and the compressive strength is non-linear, suggesting that there is potential for improving the compressive strength by increasing the silane coupling ratio to over 94.4% [25].

The functionalization of fillers with thiourethane oligomer silanes [26] could potentially serve as an alternative to functionalization with 3-methacryloxypropyl trimethoxysilane (γ -MPS), which is the gold standard silane coupling agent in dentistry.

Lee *et al.* [27] developed an *in vitro* and *in silico* approach to predict the silane coupling ratios of CAD/CAM resin composites. After immersing a CAD-CAM resin composite (Katana Avencia Block, Kuraray Noritake Dental, Niigata, Japan) in water for seven days, the predicted silane coupling ratio decreased from 78.2% to 68.4%, suggesting that 9.8% of the silane coupling layer was hydrolyzed [27]. A hydrophobic silane coupling agent [28] may be useful in inhibiting the degradation of CAD-CAM resin composites.

Concerning filler contents, Nguyen *et al.* [29] conducted an analysis on experimental CAD-CAM resin composites and affirmed that an increase in filler content led to enhanced mechanical properties. Ling *et al.* [30] reported that a relatively high loading (82.5 wt%) of a novel experimental block also augments flexural strength. It is important to note that in literature, filler content is occasionally represented in volume fraction and predominantly in weight percentage. This inconsistency in measurement units hinders direct comparisons among different products.

In relation to the filler compositions, fillers can be synthesized from various raw materials that contain elements such as Si, O, Al, Ba, Zr, and C [31–33]. This is based on both findings from literature and technical information provided by individual manufacturers. However, only a limited number of studies have explored the influence of specific filler types on the mechanical properties of CAD-CAM resin composites [23].

With respect to monomer compositions, Nguyen *et al.* [29] reported that when fillers were kept constant, urethane dimethacrylate (UDMA) used independently exhibited superior flexural strength compared to a mixture of different ratios of UDMA and triethylene glycol dimethacrylate (TEGDMA). Furthermore, Szczesio *et al.* [34] suggested that monomer mixtures of UDMA/ ethoxylated bisphenol A-glycol dimethacrylate (Bis-EMA)/TEGDMA are characterized by higher flexural strength compared to UDMA/TEGDMA. Li *et al.* [23] successfully predicted the flexural strength of CAD-CAM resin composites and identified the effective components that affected flexural strength using a ML approach on an available data set. According to the exhaustive search

S. Yamaguchi et al.

and feature importance analysis, the combination of certain components was narrowed down to achieve a flexural strength of 269.5 MPa. The corresponding chemical compositions for the flexural strength mentioned above were SiO₂, barium glass, methacrylate mixed filler, with or without Al_2O_3 for fillers, and UDMA used independently for monomers. At the same time, the filler content ranged from 82 to 85 wt %.

The overall relationship between filler content, types of fillers, and monomers used in relation to the flexural strength of CAD-CAM resin composites seems to present a non-monotonic and nonlinear problem that necessitates further investigation. The ML approach, along with *in vitro* experiments, holds significant potential as a crucial tool for identifying effective components to modify the mechanical properties of CAD-CAM resin composites, provided that a sufficient dataset is available.

4. Fracture behavior analysis

Fractographic analysis has been utilized to investigate the fracture behavior of CAD-CAM composite crowns, which is led by occlusal wear and fatigue fracture [13,35]. However, determining the fracture origin and its dynamic propagation, which are essential for understanding clinical failure, remains challenging. Yamaguchi *et al.* [20] clarified the fracture origin of CAD-CAM composite crowns and the order of crack initiation among the tested products using an *in vitro* and *in silico* approach. This approach is useful for analyzing the fracture behavior of CAD-CAM composite crowns using various preparation designs, loading conditions, and occlusal contacts that coincide with clinical situations.

The fracture origin was initiated by a concentration of tensile stress (maximum value of maximum principal stress) at the lingual side of the CAD-CAM composite crown for the restoration of the mandibular right first molar. Subsequently, the cement layer at the lingual side fractured. The order of fracture depends on the material properties of each component for a compression test. The *in silico* non-linear FEA successfully detected the sign of the initial crack of the CAD-CAM composite crown due to the high calculation cycle, while the *in vitro* experiment with the crosshead speed of 1.0 mm/sec did not show such a sign in the load-displacement curve.

The elastic modulus is one of the material parameters required to conduct the in silico non-linear dynamic FEA. In the case of CAD-CAM resin composites, the in vitro three-point bending test is conducted to evaluate flexural properties due to the limited block dimension. However, the flexural modulus obtained from the three-point bending test is not equal to the elastic modulus obtained from the tensile test, which is required for the FEA. Thus, Yamaguchi et al. [20] established an in silico model to mimic the *in vitro* fracture behavior by the three-point bending test of each component for a compression test of the CAD-CAM composite crown. The in vitro and in silico approach was available for fracture toughness tests [19], biaxial flexural strength tests [36], tensile tests [37], and shear tests [37], not only the three-point bending test. This approach can be used to assess other key properties, such as edge strength [38], to characterize clinically related behavior. The guidelines provided by the Academy of Dental Materials [39] can serve as a reference for further consideration on CAD-CAM resin composites. The digital twin [40] of these in vitro specimens will accelerate the digital transformation of in vitro testing.

Step-stress accelerating life testing, which mimics mouth-motion and sliding contact, is reliable for predicting the longevity (reliability and failure mode) of porcelain–zirconia all-ceramic crowns [41], yttria-tetragonal zirconia polycrystals crowns [42], and CAD-CAM resin composites [43]. Yamaguchi *et al.* [18] revealed that CAD-CAM resin composite molar crowns containing nanofillers (62 wt%/55 vol%) with a high fraction of resin matrix demonstrated great longevity. However, the low elastic modulus and the high fraction of the resin matrix lead to transverse expansion, which tends to spread the crown margin leading to the destruction of the adhesive interface [15,16], while it contributes

to improving the fracture toughness of CAD-CAM resin composites. The trade-off between the low elastic modulus and great longevity should be resolved for the further development of CAD-CAM resin composites. To solve this trade-off, an adaptive experimental design method with Bayesian optimization as an MI approach [24] or the combination with Taguchi's method and the genetic algorithm [44] will be useful for finding effective components of CAD-CAM resin composites. A repetitive cycle of the *in vitro* experiments and the feedback of results to the developed AI improve the prediction accuracy of AI. It is effective for finding unknown components hidden in the extrapolate region to achieve desirable performance. To obtain reliable prediction results from such AI, it is important to utilize unified input data that aligns with *in vitro* test settings (*e.g.*, specimen dimensions and testing speed), following standards such as ISO, ASTM, ANSI/ADA, and DIN.

5. Clinical implications and potential

The exceptional fracture toughness of CAD-CAM resin composites has brought significant benefits to pediatric dentistry. In this field, primary posterior teeth with extensive caries have traditionally been restored with ready-made full metal crowns due to their superior mechanical properties compared to resin composites. However, due to their non-aesthetic appearance, parents may prefer to avoid stainless steel crown restoration for their children.

Nakase *et al.* [45] developed a CAD-CAM resin composite that incorporates surface pre-reacted glass (S-PRG) filler [46] for primary teeth crowns. This composite demonstrated promising physical properties and wear resistance, exhibiting greater fracture toughness and wear resistance compared to a commercially available CAD-CAM resin composite and two resin composites designed for primary teeth.

The high fracture toughness of this composite is particularly useful for the restoration of thin primary molar teeth. It contributes to clinically acceptable fatigue behavior and bonding performance, even when glass ionomer cement is used as a luting material [47].

6. Summary

This paper summarized the effective components of CAD-CAM resin composites for their further development. The integration of *in vitro* and *in silico* approaches will expedite the advancement of CAD-CAM resin composites, offering benefits such as time efficiency and reduction of material waste for researchers and manufacturers.

Acknowledgements

This work did not receive any specific grants from funding agencies in the public, commercial, or not-for-profit sectors. The content of this paper was derived from the lecture I was invited to deliver at the 2023 Annual Meeting of the Academy of Dental Materials (ADM). We express our gratitude to Dr. Milena Cadenaro and the members of the ADM board for providing us with the opportunity to disseminate our research on CAD-CAM resin composites.

References

- Mormann WH. The origin of the Cerec method: a personal review of the first 5 years. Int J Comput Dent 2004;7:11–24.
- [2] Duret F, Blouin JL, Duret B. CAD-CAM in dentistry. J Am Dent Assoc 1988;117: 715–20.
- [3] Rekow ED. Computer-aided design and manufacturing in dentistry: a review of the state of the art. J Prosthet Dent 1987;58:512–6.
- [4] Rekow ED. Dental CAD/CAM systems: a 20-year success story. J Am Dent Assoc 2006;137(Suppl):5S–6S.
- [5] Gupta TK, Lange FF, Bechtold JH. Effect of stress-induced phase-transformation on properties of polycrystalline zirconia containing metastable tetragonal phase. J Mater Sci 1978;13:1464–70.
- [6] Bonfante EA, Coelho PG, Guess PC, Thompson VP, Silva NR. Fatigue and damage accumulation of veneer porcelain pressed on Y-TZP. J Dent 2010;38:318–24.

S. Yamaguchi et al.

Dental Materials xxx (xxxx) xxx

- [7] Lubauer J, Belli R, Peterlik H, Hurle K, Lohbauer U. Grasping the lithium hype: insights into modern dental Lithium Silicate glass-ceramics. Dent Mater 2022;38: 318–32.
- [8] Koller M, Arnetzl GV, Holly L, Arnetzl G. Lava ultimate resin nano ceramic for CAD/ CAM: customization case study. Int J Comput Dent 2012;15:159–64.
- [9] Ruse ND, Sadoun MJ. Resin-composite blocks for dental CAD/CAM applications. J Dent Res 2014;93:1232–4.
 [10] Nguyen JF, Migonney V, Ruse ND, Sadoun M. Resin composite blocks via high-
- [10] Presult in the interval of the interva
- [11] Okada K, Kameya T, Ishino H, Hayakawa T. A novel technique for preparing dental CAD/CAM composite resin blocks using the filler press and monomer infiltration method. Dent Mater J 2014;33:203–9.
- [12] Inomata M, Harada A, Kasahara S, Kusama T, Ozaki A, Katsuda Y, et al. Potential complications of CAD/CAM-produced resin composite crowns on molars: a retrospective cohort study over four years. PLoS One 2022;17:e0266358.
- [13] Lohbauer U, Belli R, Cune MS, Schepke U. Fractography of clinically fractured, implant-supported dental computer-aided design and computer-aided manufacturing crowns. SAGE Open Med Case Rep 2017;5. 2050313×17741015.
- [14] Kabetani T, Ban S, Mine A, Ishihara T, Nakatani H, Yumitate M, et al. Four-year clinical evaluation of CAD/CAM indirect resin composite premolar crowns using 3D digital data: discovering the causes of debonding. J Prosthodont Res 2022;66: 402–8.
- [15] Ankyu S, Nakamura K, Harada A, Inagaki R, Katsuda Y, Kanno T, et al. Influence of microscale expansion and contraction caused by thermal and mechanical fatigue on retentive strength of CAD/CAM-generated resin-based composite crowns. J Mech Behav Biomed Mater 2018;86:89–97.
- [16] Rosentritt M, Preis V, Behr M, Hahnel S. Influence of preparation, fitting, and cementation on the vitro performance and fracture resistance of CAD/CAM crowns. J Dent 2017;65:70–5.
- [17] Yamaguchi S, Inoue S, Sakai T, Abe T, Kitagawa H, Imazato S. Multi-scale analysis of the effect of nano-filler particle diameter on the physical properties of CAD/CAM composite resin blocks. Comput Methods Biomech Biomed Eng 2017;20:714–9.
- [18] Yamaguchi S, Kani R, Kawakami K, Tsuji M, Inoue S, Lee C, et al. Fatigue behavior and crack initiation of CAD/CAM resin composite molar crowns. Dent Mater 2018; 34:1578–84.
- [19] Karaer O, Yamaguchi S, Nakase Y, Lee C, Imazato S. In silico non-linear dynamic analysis reflecting in vitro physical properties of CAD/CAM resin composite blocks. J Mech Behav Biomed Mater 2020;104:103697.
- [20] Yamaguchi S, Katsumoto Y, Hayashi K, Aoki M, Kunikata M, Nakase Y, et al. Fracture origin and crack propagation of CAD/CAM composite crowns by combining of in vitro and in silico approaches. J Mech Behav Biomed Mater 2020; 112:104083.
- [21] Yamaguchi S, Lee C, Karaer O, Ban S, Mine A, Imazato S. Predicting the debonding of CAD/CAM composite resin crowns with AI. J Dent Res 2019;98:1234–8.
- [22] Lee JH, Kim DH, Jeong SN, Choi SH. Diagnosis and prediction of periodontally compromised teeth using a deep learning-based convolutional neural network algorithm. J Periodontal Implant Sci 2018;48:114–23.
- [23] Li H, Sakai T, Tanaka A, Ogura M, Lee C, Yamaguchi S, et al. Interpretable AI explores effective components of CAD/CAM resin composites. J Dent Res 2022; 101:1363–71.
- [24] Yamaguchi S, Li H, Imazato S. Materials informatics for developing new restorative dental materials: a narrative review. Front Dent Med 2023;4.
- [25] Lee C, Kashima K, Ichikawa A, Yamaguchi S, Imazato S. Influence of hydrolysis degradation of silane coupling agents on mechanical performance of CAD/CAM resin composites: In silico multi-scale analysis. Dent Mater J 2020;39:803–7.
- [26] Goulart M, Fugolin AP, Lewis SH, Rodrigues JA, Erhardt MC, Pfeifer CS. Thiourethane filler functionalization for dental resin composites: concentrationdependent effects on toughening, stress reduction and depth of cure. Mater Sci Eng C Mater Biol Appl 2021;118:111535.

- [27] Lee C, Yamaguchi S, Imazato S. Quantitative evaluation of the degradation amount of the silane coupling layer of CAD/CAM resin composites by water absorption. J Prosthodont Res 2023;67:55–61.
- [28] Nihei T, Dabanoglu A, Teranaka T, Kurata S, Ohashi K, Kondo Y, et al. Three-bodywear resistance of the experimental composites containing filler treated with hydrophobic silane coupling agents. Dent Mater 2008;24:760–4.
- [29] Nguyen JF, Migonney V, Ruse ND, Sadoun M. Properties of experimental urethane dimethacrylate-based dental resin composite blocks obtained via thermopolymerization under high pressure. Dent Mater 2013;29:535–41.
- [30] Ling L, Ma Y, Malyala R. A novel CAD/CAM resin composite block with high mechanical properties. Dent Mater 2021;37:1150–5.
- [31] Papathanasiou I, Kamposiora P, Dimitriadis K, Papavasiliou G, Zinelis S. In vitro evaluation of CAD/CAM composite materials. J Dent 2023;136:104623.
- [32] Hampe R, Lumkemann N, Sener B, Stawarczyk B. The effect of artificial aging on Martens hardness and indentation modulus of different dental CAD/CAM restorative materials. J Mech Behav Biomed Mater 2018;86:191–8.
- [33] Koenig A, Schmidtke J, Schmohl L, Schneider-Feyrer S, Rosentritt M, Hoelzig H, et al. Characterisation of the filler fraction in CAD/CAM Resin-based composites. Mater (Basel) 2021;14.
- [34] Szczesio-Włodarczyk A, Domarecka M, Kopacz K, Sokolowski J, Bociong K. An evaluation of the properties of urethane dimethacrylate-based dental resins. Mater (Basel) 2021;14.
- [35] Saratti CM, Rocca GT, Durual S, Lohbauer U, Ferracane JL, Scherrer SS. Fractography of clinical failures of indirect resin composite endocrown and overlay restorations. Dent Mater 2021;37:e341–59.
- [36] Li H, Yamaguchi S, Lee C, Benalcazar-Jalkh EB, Bonfante EA, Imazato S. In silico nonlinear dynamic finite-element analysis for biaxial flexural strength testing of CAD/CAM materials. J Prosthodont Res 2024.
- [37] Kawashima M, Yamaguchi S, Mine A, Li H, Imazato S. Novel testing method to evaluate the mechanical strength of self-adhesive resin cements with reflection of cement thickness. Dent Mater J 2021;40:1235–42.
- [38] Pfeilschifter M, Preis V, Behr M, Rosentritt M. Edge strength of CAD/CAM materials. J Dent 2018;74:95–100.
- [39] Ilie N, Hilton TJ, Heintze SD, Hickel R, Watts DC, Silikas N, et al. Academy of dental materials guidance-resin composites: part I-mechanical properties. Dent Mater 2017;33:880–94.
- [40] Lee JH, Lee HL, Park IY, On SW, Byun SH, Yang BE. Effectiveness of creating digital twins with different digital dentition models and cone-beam computed tomography. Sci Rep 2023;13:10603.
- [41] Coelho PG, Silva NR, Bonfante EA, Guess PC, Rekow ED, Thompson VP. Fatigue testing of two porcelain-zirconia all-ceramic crown systems. Dent Mater 2009;25: 1122–7.
- [42] Bonfante EA, Sailer I, Silva NR, Thompson VP, Rekow ED, Coelho PG. Failure modes of Y-TZP crowns at different cusp inclines. J Dent 2010;38:707–12.
- [43] Shembish FA, Tong H, Kaizer M, Janal MN, Thompson VP, Opdam NJ, et al. Fatigue resistance of CAD/CAM resin composite molar crowns. Dent Mater 2016; 32:499–509.
- [44] Cahyanto A, Rath P, Teo TX, Tong SS, Malhotra R, Cavalcanti BN, et al. Designing calcium silicate cements with on-demand properties for precision endodontics. J Dent Res 2023. 220345231198185.
- [45] Nakase Y, Yamaguchi S, Okawa R, Nakano K, Kitagawa H, Imazato S. Physical properties and wear behavior of CAD/CAM resin composite blocks containing S-PRG filler for restoring primary molar teeth. Dent Mater 2022;38:158–68.
- [46] Imazato S, Nakatsuka T, Kitagawa H, Sasaki JI, Yamaguchi S, Ito S, et al. Multipleion releasing bioactive Surface Pre-Reacted Glass-Ionomer (S-PRG) filler: innovative technology for dental treatment and care. J Funct Biomater 2023;14.
- [47] Nakase Y, Yamaguchi S, Jalkh EBB, Atria PJ, Witek L, Bonfante EA, et al. In vitro analysis of durability of S-PRG filler-containing composite crowns for primary molar restoration. Dent Mater 2023;39:640–7.